


JERUSALEM STONE | CHOCOLATE

Wild moss-colored stone with white veins and reddish intrusions. An elegant proposal for areas that want to give prestige. This color can be easily combined with other NASSAR STONE colors.



Broached



Honed



Brushed



Polished



Furrowed



Stugged

Test	Specification	Result
Water Absorption (%)	ASTM C97	0.32
Bulk Specific Gravity (Gr/cm3)	ASTM C97	2.737
Compressive Strength (Mpa)	ASTM C170	Perpend. to rift: Wet: 143.7 Dry: 100.7 Parallel to rift: Wet: 117.7 Dry: 136.2
Modulus of Rupture (N/mm2)	ASTM C99	Perpend. to rift: Wet: 12.2 Dry: 13.7 Parallel to rift: Wet: 13.8 Dry: 13.0
Flexural Strength (N/mm2)	ASTM C880	Wet: 6.3 Dry: 8.5
Abrasion Resistance (N/mm2)	ASTM C241	35.6