




JERUSALEM STONE | GOLD VEIL

A warm off-white limestone accented with a hint of red streaks and fossil intrusions. The variety of finishes allows combinations according to the needs of the project or the creativity of the designer.



60X60




cut-to-size



Brushed



Polished



Bush Hammered



Rough Bush Hammered



Honed



Stugged

Test	Specification	Result
Water Absorption (%)	ASTM C97	0.98
Bulk Specific Gravity (Gr/cm3)	ASTM C97	2.613
Compressive Strength (Mpa)	ASTM C170	Perpend. to rift: Wet: 71.8 Dry: 88.5 Parallel to rift: Wet: 86.4 Dry: 100.1
Modulus of Rupture (N/mm2)	ASTM C99	Perpend. to rift: Wet: 3.7 Dry: 6.1 Parallel to rift: Wet: 10.3 Dry: 8.4
Flexural Strength (N/mm2)	ASTM C880	Wet: 7.8 Dry: 8.0
Abrasion Resistance (N/mm2)	ASTM C241	20.2