
## NASSAR I STONE



## OMANI MARBLE | **DELICATE NATURAL**

A beige brown marble with inherent veins, crystal shapes and rose patches. Create surfaces full of personality. Marble in a polished and honed finish is ideal for interior cladding and flooring. On the other hand, aged marble, bushhammered is more appropriate for outpring. for exteriors.











Bush Hammered

Test	Specification	Result
Water Absorption (%)	ASTM C97	0.26
Bulk Specific Gravity (Gr/cm3)	ASTM C97	2.681
Compressive Strength (Mpa)	ASTM C170	Perpend. to rift: <b>Wet:</b> 100.8 <b>Dry:</b> 100.9 Parallel to rift: <b>Wet:</b> 106.2 <b>Dry:</b> 106.6
Modulus of Rupture (N/mm2)	ASTM C99	Perpend. to rift: <b>Wet:</b> 9.0 <b>Dry:</b> 8.2 Parallel to rift: <b>Wet:</b> 8.0 <b>Dry:</b> 8.8
Flexural Strength (N/mm2)	ASTM C880	<b>Wet:</b> 7.9 <b>Dry:</b> 7.2
Abrasion Resistance (N/mm2)	ASTM C241	28.6