



JERUSALEM STONE | BUTTER SILK

Light yellowish cream limestone with a soft and warm appearance and some fossil content. Its characteristic color makes it highly appreciated in high-traffic areas.



cut-to-size



Brushed



Natural
Split Face



Honed



Polished

Test	Specification	Result
Water Absorption (%)	ASTM C97	0.72
Bulk Specific Gravity (Gr/cm3)	ASTM C97	2.628
Compressive Strength (Mpa)	ASTM C170	86 N/mm2
Modulus of Rupture (N/mm2)	ASTM C99	Perpend. to rift: 10.87 Parallel to rift: 11.19
Flexural Strength (N/mm2)	ASTM C880	Perpend. to rift: 13.96 Parallel to rift: 12.52
Abrasion Resistance (N/mm2)	ASTM C241	13.57